

地毯胶是专为耐用的室内地毯和双向固定的安装设计的一款胶。**地毯胶**可以使背面坚硬的地毯进行很强的黏结。该胶粘剂可以延长其黏合时间，低气味且环保。Carpet Stix Carpet Adhesive is designed for tough interior carpet and dual bond installations. Carpet Stix forms a powerful bond with stiff-backed carpets. This adhesive remains tacky for an extended period of time, is low odor and environmentally friendly.

安装场地必须在能适应的 HVAC 的工作环境中进行。请确保在测试前及测试，安装和安装后的这 48 个小时时间，地板和房间的温度，以及地板材料和组合胶都必须保持在 18.3°C - 35°C，湿度在 65%以下。按照地板覆盖制造商的安装说明和适当的胶粘剂应用率。The installation site must be acclimated with HVAC in operation. The floor and room temperature, as well as flooring materials and adhesive, must be maintained at 18.3°C - 35°C, and the humidity below 65% for 48 hours prior to, during, and after the testing and installation. Follow floor-covering manufacturer's installation instructions and proper adhesive application rate. 混凝土基材应采用 ASTM F1869 的测试方法，氯化钙的水蒸气排放率（MVER），或 ASTM F2170 的现场相对湿度。表面 pH 值不得超过 9。混凝土基材水蒸气排放率必须低于 5 磅，或 ASTM F2170 的现场相对湿度应低于 80%。现场条件，地面准备，湿度和碱度必须符合美国地毯协会(CRI : Carpet & Rug Institute)的规定 (CRI 104 or 105). Concrete substrates must be tested for moisture vapor emissions rate (MVER) per Calcium Chloride Test Method ASTM F1869, or for in-situ Relative Humidity per ASTM F2170. The surface pH must not exceed 9.0. MVER of concrete substrates must be below 5.0 lbs., or with in-situ Relative Humidity below 80% per ASTM F2170. Site conditions, floor preparations, and moisture and alkalinity must comply with those specified by the Carpet & Rug Institute (CRI 104 or 105). 地面必须有完好无损，光滑，干燥和干净。为了确保组合胶的黏合效果，请清除污垢，蜡，油漆和所有的外来物质。不要使用过多的胶粘剂或化学清洗表面。将容易渗透，或者有灰尘的水泥表面用合适的密封剂将其密封好。为了保证 100%转移到地毯的背面，必须确保当地毯铺设到粘合剂上时，粘合剂仍然是湿的，用 75-100 磅（34 - 45.4 公斤）的辊子进行滚动。当安装在一个非多孔的表面时，会让胶变得很黏。如需详细安装说明，请参阅技术数据表。The floor must be sound, smooth, dry and clean. Remove and dirt, wax, loose paint and all foreign matter that would interfere with a good bond. Seal porous or dusty concrete surfaces. Lay carpet into adhesive that is still wet enough to ensure 100% transfer to the carpet backing, and roll with a 75-100 lbs. (34.0 – 45.4 kg) roller. When installing over a non-porous surface, let adhesive become tacky. Refer to Technical Data Sheet for detailed installation instructions.

**类型 Type:**  
· 不可溶解，无危害，水性胶粘剂。Solvent Free, non-hazardous, water based adhesive.  
· “零”克/升的挥发性有机化合物（VOC 的计算）“Zero” grams/Liter Volatile Organic Compounds (calculated VOC's).

**优点 Advantages:**  
· 非常快，很强的粘附力 Very quick, strong bond development.  
· 通过 CRI Green Label Plus 的认证. CRI Green Label Plus Approved  
· 可用于防潮板的上面或者下面 May be used on moisture free slabs above below, or on grade  
· 当湿了可用水来清洁 Water clean up when wet  
· 低气味：没有刺鼻的气味来破坏安进行 Low odor – No annoying odors to disrupt the installation.

**干燥时间 Open Time:**  
取决于使用时的工作环境，15 分钟至 25 分钟 15 to 25 minutes. Dependent upon atmospheric conditions

**抹子尺寸 Trowel Size:**  
正常使用（涤纶，黄麻背面）：3 / 32"x3 / 32"x3 / 32"V 型缺口镬刀  
（2.4mmx2.4mmx2.4mm V 型缺口抹子，2.21 - 3.31 平方米 / 升）  
Normal use (Action Bac, jute): 3 / 32"x3 / 32"x3 / 32" V- notched trowel:  
（2.4mmx2.4mmx2.4mm V- notched trowel, 2.21 - 3.31 square meters/litre）  
粗糙的背面或粗糙的地板：1 / 8"x1 / 8"x1 / 16"U 型锯齿镬刀  
（3.2mmx3.2mmx1.6mm的 U 型缺口抹子，1.10 – 1.77 平方米 / 升）  
Rough back or Rough Floor: 1 / 8"x1 / 8"x1 / 16" U-notched trowel.  
（3.2mmx3.2mmx1.6mm的 U-notched trowel, 1.10 – 1.77 square meters/litre）

**存放时间 Shelf Life:**  
在适当的储存容器中，未开封的情况下，以制造日期为基准，可存放 2 年。  
2 years from manufacturing date, in an unopened container

**适用于 Uses:**  
涤纶背面，黄麻背面，橡胶背面，编织背面  
Action Bac@Jute Back, Rubber Back,Woven Back  
此粘合剂不建议用于固体的乙烯基或乙烯基泡沫的背面  
This adhesive is not recommended for solid vinyl or vinyl foam backing.  
本产品已被加利福尼亚的 102 和 443 条款列为不会光化学反应的产品。  
This product is not photochemically reactive as defined by California Rules 102 and 443.  
VOC 的含量也低于加利福尼亚 SCAQMD 1168 的条款  
VOC content is below that established by California SCAQMD Rule 1168.  
在使用前，安装人员应确定该产品的适用性  
Before using, the installer shall determine the suitability of the product for intended use.



# Carpet Stix

## 地毯胶

### Carpet Adhesive

不溶解，低气味

SOLVENT FREE ADHESIVE  
Low Odour  
CRI Green Label Plus Approved

Manufactured by an ISO 14001:2004 EMS Certified Supplier

15.14 Litres



**24-Hour Emergency:**  
**Poisons Information Centre:**  
**USA: 1-800-424-9300**

**成份信息 Composition Information:**  
无危险成份 100% Non-hazardous Ingredients - 100%

**危险源辨识 Hazardous Identification:**  
根据 ASCC 和 ADG Code 的准则，不被列为危险产品 Not classified as hazardous according to ASCC Criteria. Not Classified as dangerous goods by the criteria of the ADG Code.

**火源和爆炸危险数据 Fire and Explosion Hazard Data:**  
易燃性：本产品被列为非易燃  
Flammability Classification: Non-flammable  
闪点：不具备  
Flash Point: Not Relevant  
灭火装备：二氧化碳，化学泡沫，水雾  
Extinguishing Media: CO<sub>2</sub>, chemical foam, water fog.

**特殊消防功能 Special Fire Fighting Features:**  
在密闭区域内佩戴自给式呼吸器 Wear self-contained breathing gear when in confined area.

**急救和急救程序 Emergency and First Aid Procedure:**  
眼睛：如果在眼睛里，把眼皮分开，然后用自来水冲洗 15 分钟  
Eye: If in eyes, hold eyelids apart and flush with running water for 15 minutes.  
皮肤：用肥皂和水进行清洗  
Skin: Wash with soap and water.

**Ingestion:** Contact Poisons Information Centre on  
USA: 1-800-424-9300 or a doctor.

**处理和使用的注意事项 Precautions for Handling and Use:**  
通风：局部通风 Ventilation: Local ventilation.  
保护手套：建议使用 Protective Gloves: Recommended  
护眼：安全眼镜 Eye Protection: Safety Glasses.  
卫生习惯：在曝光后，用肥皂和水进行清洗  
Hygienic Practices: Wash with soap & water after exposure.  
呼吸防护：不需要有足够的通风  
Respiratory Protection: Not required with adequate ventilation.  
其他防护设备：无 Other Protective Equipment: none.

溢出：用惰性吸附剂覆盖小的溢物，然后清理和放置在处理容器中。按照当地政府的规定处理  
Spills: Cover small spills with inert absorbent, then sweep up and place in waste disposal container. Dispose of in accordance with Federal, State and Local regulations.

**储存 Storage:**  
储存在阴凉、干燥、通风的地方。温度在 15° C 和 37° C 之间，本产品不可以冷冻。  
Store in a cool, dry, ventilated area. Store between 15°C and 37°C. Do not allow product to freeze.

**信息 Note:**  
更多相关信息请参考技术和材料安全数据表  
Refer to technical and material safety data sheets for more information.

**www.universalflooringsolutions.com**  
**美国制造 Made in USA**

121709